

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 November 2001 (08.11.2001)

PCT

(10) International Publication Number
WO 01/83887 A1

(51) International Patent Classification⁷: **D21H 21/20**,
C08B 15/00, 31/00 // D21H 17:25, 17:28

(74) Agent: **JORRITSMA, Ruurd**; Nederlandsch Octrooi-
bureau, Scheveningsweg 82, P.O. Box 29720, NL-2502 LS
The Hague (NL).

(21) International Application Number: PCT/NL01/00343

(22) International Filing Date: 4 May 2001 (04.05.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00201630.1 4 May 2000 (04.05.2000) EP
00201693.9 11 May 2000 (11.05.2000) EP

(71) Applicant (for all designated States except US): **SCA
HYGIENE PRODUCTS ZEIST B.V.** [NL/NL]; P.O. Box
360, NL-3700 AJ Zeist (NL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **THORNTON,
Jeffrey, Wilson** [US/NL]; Jagersweg 13, NL-1272 AC
Huizen (NL). **VAN BRUSSEL-VERRAEST, Dorine,**
Lisa [BE/NL]; Kopeind 1, NL-2411 WG Bodegraven
(NL). **BESEMER, Arie** [NL/NL]; Burg. Jhr. H. v.d.
Boschstraat 111, NL-3958 CE Amerongen (NL). **SAND-
BERG, Sussan** [SE/SE]; Gubbekullavägen 15, S-439 35
Onsala (SE).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: **ALDEHYDE-CONTAINING POLYMERS AS WET STRENGTH ADDITIVES**

(57) Abstract: The invention concerns the use of a water-soluble or water-dispersible polymer having a molecular weight of at least 800, containing at least 5 aldehyde groups per molecule and at least 1 carboxyl group per molecule, the ratio of aldehyde groups to carboxyl groups being higher than 0.75:1, as a wet strength additive. The invention also discloses novel cationic derivatives thereof.

Aldehyde-containing polymers as wet strength additives.

5 [0001] The present invention relates to the use of multifunctional aldehyde-containing polymers as temporary wet strength agents for paper and tissue applications, as well as non-wovens.

[0002] Wet strength is an important characteristic of paper and tissue products, and in non-woven products. Wet strength of such products can be increased by using wet strength additives. The most widely used wet strength additives for the paper industry are melamine-formaldehyde and urea-formaldehyde. There is a tendency, however, to move away from
10 such oil-based chemicals, because they are not renewable and have a poor biodegradability. Carboxymethyl cellulose (CMC) is currently used in combination with PAE (polyamino-amide epichlorohydrin) as a wet strength agent (see Espy, TAPPI Journal, 78, 90 (1995)). However, CMC is also partly dependent on oil-based materials (monochloroacetic acid) and, moreover, is a rather expensive material.

15 [0003] Oxidised celluloses have the advantage of being accessible from renewable raw materials only and possibly of being less expensive than CMC, while they may have comparable properties to CMC. However, the oxidation of cellulose is hampered by the poor solubility of cellulose, making it insufficiently accessible to oxidising agents.

[0004] Aldehyde functions have been recognised as being useful in binding cellulose
20 fibers, to improve wet strength of the fibers. Thus, dialdehyde starch (TAPPI, 57, 81 (1974); and TAPPI 45, 750 (1962)) and dialdehyde guar and the like (WO 97/36054) have been proposed as paper wet strength additives. US 3,087,852 and US 4,001,032 disclose cationic dialdehyde starch, obtained by reacting dialdehyde starch with betaine hydrazide, to be used as a paper strengthening additive.

25 [0005] US 5,935,383 discloses the use of anionic compounds, such as sulphato-ethyl-amino-halotriazines, for providing the cellulose surface with additional anionic sites suitable for retaining a high proportion of cationic wet strength additives such as PAE resin on the cellulose.

[0006] WO 99/23117 and WO 99/23240 describe the oxidation of cellulose and starch,
30 respectively, with TEMPO and an oxidative enzyme (laccase) and oxygen at pH 4-9 resulting in products containing low levels of carbaldehyde and carboxyl groups.

[0007] US 3,553,193 describes the oxidation of starch with bromite or hypobromite, which results in varying levels of carbonyl (ketonic) and carboxyl groups depending on the oxidation conditions, with a carbonyl/carboxyl ratio of between 2:1 and 8:1. The oxidation
35 products are stated to be suitable as paper strength additives. The oxidation of starch with sodium hypochlorite is believed first to yield keto groups. In a later stage of oxidation

aldehyde groups may be formed. The mechanism postulated by Whistler (J. Am. Chem. Soc., 79, 6460 (1957), see also PhD thesis of Floor, Delft University of Technology, 1989) however states that a diketo group is formed, which decomposes with OH⁻ and is oxidised. One has to assume that hypobromite reacts in an analogous way. A recent publication of Deary and Davies in Carbohydr. Research 309, 17-29 (1998) reviews the bromine oxidation and confirms that keto groups are the primary products from bromine oxidation. From their experiments with α -cyclodextrins they conclude also that the keto product is formed. They present no evidence for the formation of aldehydes. Also, Torneport et al (Starch 42, 413-417 (1990)) and Salomonsson et al (Carbohydrate Res. 217 (1991)) state that oxidation of starch with bromine species ($\text{Br}_2:\text{CH} = 1/40$ to $1/1$) at pH 7 results in keto groups and carboxylic acids. It is known that higher pH's lead to higher carboxylate contents.

[0008] It was found that multifunctional polymers, especially biopolymers, having both aldehyde functions and carboxylic acid and/or other anionic functions, the ratio between aldehyde functions and anionic functions (hereafter referred to as A/C ratio) being at least 0.75:1, preferably at least 2:1, up to about 15:1, preferably up to 10:1, are very useful as wet strength additives. These polymers are excellent substitutes for known wet strength agents such as carboxymethyl cellulose (CMC) and dialdehyde starch because of their better ecological acceptability (degradability) and their improved water-solubility and thus better accessibility to further reagents, and an improved functionality.

[0009] The polymers to be used can be of a synthetic type, such as a copolymer of acrylic acid and acrolein, a copolymer of maleic acid and maleic (mono)aldehyde, appropriately modified polyvinyl alcohol or appropriately (aldehyde-)substituted polyacrylic acid or the like, having the desired level of aldehyde groups and the desired A/C ratio.

[0010] It is preferred, however, that the polymer is a biopolymer. Suitable biopolymers include (modified) peptides and proteins, proteoglycans and in particular polysaccharide-types of polymer. Examples of polysaccharides include α -1,4-glucans (the "starch family", including amylose, amylopectin, dextrans and cyclodextrins), α -1,6-glucans (dextran) and mixed α -glucans such as pullulan, β -1,4-glucans (cellulose), β -1,3-glucans such as scleroglucan and curdlan, xyloglucans, glucomannans and galactomannans (guar and locust bean gum), other gums including heterogeneous gums like xanthan, ghatti, carrageenans, alginates, pectin, (arabino)xylans (hemicellulose), β -2,1- and β -2,6-fructans (inulin and levan), etc. The biopolymers may also be synthetically modified.

[0011] The simultaneous presence of aldehyde and anionic, such as carboxyl ($-\text{CO}_2\text{H}$), sulphy ($-\text{SO}_3\text{H}$) and phosphono ($-\text{PO}_3\text{H}_2$) groups, can be achieved by various methods.

These methods comprise:

- (1) introduction of anionic groups by addition, followed by introduction of aldehyde functions, e.g. by oxidation; here, the anionic groups such as carboxyl groups or other acid groups may be introduced e.g. by carboxyalkylation, sulphatation, sulphonylation, phosphatation, or the like, or they may be present in polymers which already have added acid groups by biosynthesis such as sulphate groups in carrageenans; the aldehyde functions can be introduced e.g. by oxidation of 1,2-dihydroxyethylene groups (such as those at the 2,3-position of 1,4-linked or 1,6-linked glucans) using periodate-type oxidising agents, or by partial oxidation of hydroxymethyl groups (such as those at the 6-position of 1,4-linked or 1,3-linked glucans) using nitric oxide (NOx) types of oxidising agents;
- (2) introduction of carboxyl groups by oxidation of hydroxymethyl groups followed by introduction of aldehyde functions by oxidation as under (1); here, the carboxyl (anionic) groups are introduced by oxidation of the hydroxymethyl groups, such as those at the 6-position of 1,4-linked or 1,3-linked glucans, using NOx-type of oxidising agents, or they may be present in polymers already containing 6-carboxyl groups by biosynthesis, if necessary after hydrolysis of ester groups, such as pectins, xanthans and alginates; the aldehyde groups can again be introduced e.g. by oxidation of 1,2-dihydroxyethylene groups, or by partial oxidation of further hydroxymethyl groups;
- (3) controlled oxidation of hydroxymethyl groups (such as those at the 6-position of 1,4-linked or 1,3-linked glucans) so as to partly convert them to aldehyde functions and to convert only a (minor) part of the aldehyde functions so obtained to carboxyl functions;
- (4) introduction of aldehyde groups, e.g. by oxidation of 1,2-dihydroxyethylene groups (such as those at the 2,3-position of 1,4-linked or 1,6-linked glucans) using periodate-type oxidising agents, followed by partial further oxidation thereof to carboxyl groups using different oxidising agents such as chlorite or bromine;
- (5) introduction of (protected) aldehyde groups (e.g. furan acetals) by etherification, e.g. as described in US 4,731,162 and US 4,741,804, followed by introduction of carboxymethyl groups.
- Further combinations of partial reaction steps as described above are also contemplated.
- [0012] The individual reaction steps referred to above are known in the art. Carboxymethylation of polysaccharides is also widely used in the art, and is commonly performed using sodium monochloroacetate in alkaline medium or by hydroxyalkylation (e.g. with ethylene oxide) followed by catalytic oxidation. Other carboxyalkylation, such as carboxyethylation, can be accomplished by base-catalysed addition of acrylamide followed by hydrolysis, or by addition of succinic or maleic or other anhydride, etc. Sulphate and sulphonylation

groups can be introduced by reaction with sulphuric acid derivatives such as chloro-sulphonic acid or with vinylsulphonic acid or taurine analogues. Phosphorylation can be achieved by reaction with phosphoric acid or its derivatives or with haloalkyl-phosphonic acids.

- 5 [0013] Also, oxidation of 1,2-dihydroxyethylene groups in the recurring units of polysaccharides is extensively known, and can be performed with periodate or similar polyoxy-anions, resulting in C-C bond scission according to the equation:



- and thus to opening of the cyclic anhydromonosaccharide unit. These products are usually referred to as "dialdehyde carbohydrates" such as dialdehyde starch (DAS) and dialdehyde inulin (DAI).
- 10

- [0014] The partial further oxidation of these dialdehyde carbohydrates can be accomplished, e.g. with sodium chlorite with or without hydrogen peroxide, the molar amount of chlorite, with respect to the dialdehyde product, determining the carboxyl content of the final product.
- 15

- [0015] A particularly advantageous method of further oxidising dialdehyde carbohydrates in a partial and controlled manner is described in PCT/NL99/00673 (WO00/26257, published 11 May 2000) and proceeds by reacting the dialdehyde product with a catalytic amount of halogen, such as chlorine, iodine and especially bromine. Halogen is regenerated in situ by oxidation with an oxidising agent. Sodium hypochlorite can be used for the (re)generation of the molecular halogen, but preference is given to peracids. The catalytic amount of molecular halogen may be 0.2-40, preferably from 1 to 10 mole%, with respect to the amount of peracid. The peracid may be any peralkanoic acid such as peracetic acid, perpropionic acid, perlauric acid etc., a substituted peralkanoic acid such as peroxy-trifluoroacetic acid, an optionally substituted aromatic peracid such as perbenzoic acid or m-chloroperbenzoic acid, or an inorganic peracid such as perboric or persulphuric acid. The molar amount of oxidising agent (e.g. peracid) with respect to the dialdehyde product, determines the carboxyl content of the final product.
- 20
- 25

- [0016] This method, besides reducing the amount of halide produced, is also beneficial to the properties of the partially oxidised products, in particular as to a more regular distribution of carboxyl and aldehyde groups. In addition, this method is cheaper than the oxidation with sodium chlorite in the presence of hydrogen peroxide and produces less halide waste.
- 30

- [0017] The selective oxidation of hydroxymethyl groups (i.e. primary hydroxyl functions) to aldehyde and/or carboxyl functions has been known for several years. Nitric oxides, i.e. nitrogen dioxide and dinitrogen tetroxide or nitrite/nitrate are known in the art as suitable
- 35

oxidising agents for these oxidations, as described e.g. in US Patent 3,364,200 and NL patent application 93.01172 and by Painter, Carbohydrate Research 55, 950193 (1977) and *ibid.* 140, 61-68 (1985). This oxidation may be performed in an apolar, e.g. halogenated, solvent, or in an aqueous solvents, such as phosphoric acid.

- 5 [0018] A preferred reagent for the selective oxidation of hydroxymethyl groups is constituted by nitroxyl compounds, such as TEMPO (2,2,6,6-tetramethyl-piperidine-N-oxide) and related compounds such as 2,2,5,5-tetramethylpyrrolidine-N-oxyl, 2,2,5,5-tetramethylimidazoline-N-oxyl, and 4-hydroxy TEMPO and derivatives thereof such as the
- 10 4-phosphonooxy, 4-acetoxy, 4-benzoyloxy, 4-oxo, 4-amino, 4-acetamino, 4-maleimido, 4-isothiocyanato, 4-cyano and 4-carboxy TEMPO. TEMPO is used in these reactions as a catalyst (e.g. using 0.1-25 mol% with respect to final oxidising agent) in the presence of a final oxidising agent such as hypochlorite or hydrogen peroxide. TEMPO oxidation has been described e.g. in WO 95/07303. Further intermediate oxidants such as metal complexes (see PCT/NL00/00118 = WO 00/50388), enzymes such as laccase or per-
- 15 oxidases (see WO 99/23240 and WO 99/23117 and PCT/NL00/00117 = WO 00/50621) can be used. Examples of metal complexes are complexes of a transition metal such as manganese, iron, cobalt, nickel, copper, vanadium or ruthenium, with a complexing agent, especially nitrogen-containing compound such as a bipyridyl, a trimethyl-triazonane or other poly(tertiary amine) or a (poly)histidine; such metal complexes can be used in an
- 20 amount of 1-25 mol% with respect to the number a aldehyde or carboxyl groups desired. The actual oxidising species in the TEMPO-mediated oxidations is believed to be the nitrosonium ion. The A/C ratio can be controlled by selecting appropriate conditions: aldehyde formation is favoured at low temperatures (0-20 °C) and at relatively low pH (3-7) and by controlled addition and/or low levels of oxidising agent.
- 25 [0019] The anionic groups in the products thus obtained may be free carboxyl, sulpho or phosphono groups (acid form) or may be in the salt form, e.g. with sodium, potassium, ammonium or substituted ammonium as the counter cation. The aldehyde- and acid-containing products have at least 5 aldehyde groups, especially at least 10 aldehyde groups, and at least 1 anionic group, especially at least 3 anionic groups, such as carboxyl groups,
- 30 per molecule, also depending on the molecular weight (degree of polymerisation, DP). Thus, for smaller molecules, e.g. having a molecular weight below 3,000, the number of aldehyde groups per molecule may be lower, e.g. at least one per 600 Da, with a minimum of 2. The degree of substitution (DS) for aldehyde groups is preferably between 5 and 98 % of the maximum value, more preferably between 25 and 75%. As the maximum number of
- 35 aldehyde groups in most oxidised polysaccharides is 3 per recurring (monosaccharide) unit, the DS expressed in number of substituent groups per recurring unit is at least 0.10,

preferably between 0.15 and 2.95, more preferably between 0.25 and 2.25). The DS for anionic groups, especially carboxylic groups, is preferably between 0.03 and 1.0, more preferably between 0.05 and 0.4 per recurring unit.

[0020] If desired for the purpose of enhancing wet strength, the multifunctional product
5 can be further chemically modified. A particularly suitable derivative is a product also containing cationic groups. Such cationic groups can be introduced by reacting a part of the aldehyde groups with an amine, hydrazine, hydrazide or the like, optionally under reductive conditions, or by reacting, at some stage during the production, saccharidic hydroxyl
10 groups with ammonium-containing reagents such as trimethylammonio-alkyl halides or epoxides. These multifunctional cationic compounds contain at least 0.01 up to about 0.50 cationic groups per recurring unit, preferably from 0.02 to 0.25 cationic groups per recurring unit; they are also part of the invention.

[0021] Alternatively, the aldehyde-anionic polymers can be combined with separate cationic compounds such as, for example, cationic polysaccharides, in particular cationic
15 DAS, or with other conventional cationic wet strength agents such as PEI (polyethyleneimine) or PAE, to produce a composite wet-strength agent. The weight ratio between the aldehyde/anionic polymer and the cationic compound can be e.g. from 90:10 to 10:90, especially from 75:25 to 15:85. Such composite wet strength agents are a distinct embodiment of the invention.

[0022] The aldehyde-containing anionic polymers can be combined, usually as aqueous
20 solutions or dispersions with cellulosic fibres in a manner known for the application of wet strength agents. The amount of agent is preferably between 0.1 and 4 % by weight, especially between 0.2 and 2 % by weight, with respect to the cellulosic fibre. If desired, cationic wet strength agents can be applied subsequently followed by drying the fibre web.
25 Addition of a cationic polymer is usually necessary for multifunctional derivatives that do not themselves contain cationic groups, because otherwise there would insufficient absorption of the derivative to the fibre. Further alternate layering with aldehyde-containing anionic polymer and cationic polymer can also be advantageous.

30 Examples

Abbreviations:

6-AS: 6-aldehyde starch

DAS: dialdehyde starch

MACC: monoaldehyde-carboxy cellulose

35 MACS: monoaldehyde-carboxy starch

PAE: polyamide-amide epichlorohydrin

PCD: particle charge determination

PEI: polyethyleneimine

5 Example 1

a) Preparation of MACS with peracetic acid/bromide to different degrees of oxidation

Dialdehyde starch (oxidation degree 100%) was prepared by adding 6.6 g sodium periodate (31 mmole) to a slurry of 5.0 g (dry weight) starch (31 mmole) in 100 ml water which was brought to pH 5 with diluted acetic acid and cooled to 4°C. The mixture was stirred for 24
10 hours at 4°C in the absence of light. The obtained product was isolated by filtration and washed with water until iodate could no longer be detected by reaction with potassium iodide.

To obtain MACS, the dialdehyde starch was reslurried in 100 ml water and part of the aldehydes were further oxidised to carboxylates. To achieve this, sodium bromide (0.5 g)
15 was added and then peracetic acid (0.6 M) was added portion-wise (see Table 1). The pH was kept constant at pH 5 using 0.5 M NaOH (pH-stat.). After reaction, the aldehyde carboxy starch was purified by membrane filtration (molecular cut-off 5000 MW) and freeze-dried.

Table 1: Conversion of DAS to MACS

Sample	Totally added peracetic acid solution (ml of 0.6 M solution)	% aldehydes oxidised to carboxylates
A5	5	5
A10	10	10
A30	31	30
A50	52	50

20

b) Application as wet strength additive

The addition levels were 10 mg/g MACS and 10 mg/g PAE.

Sheets were prepared as in example 8. The results are presented in Figure 1.

The highest relative wet strength was obtained in the sheets treated with MACS with an
25 oxidation degree of 10% and PAE. The performance of this combination is better than the combination of CMC and PAE, which is commonly used nowadays. It may be noted that when no additives are used, essentially no wet strength is obtained (compare Figure 6).

Example 2

MACS with an oxidation degree of 50% was prepared as described in Example 1. This polymer was added to pulp together with PEI (3mg/g and 7mg/g, respectively).

- 5 Sheets were prepared as in example 8. The results are presented in Figure 2. It may be noted that PEI does not give wet strength by itself (like PAE does). The wet strength shown in the case of MACS + PEI can be completely ascribed to MACS.

Example 3

a) Preparation of MACS with chlorite/hydrogen peroxide to different degrees of oxidation

- 10 Dialdehyde starch (oxidation degree 100%) was prepared as described in example 1. To obtain MACS, 5 g of the dialdehyde starch (30 mmole AGU) was reslurried in 100 ml water and cooled to 4°C. In order to oxidise part of the aldehydes to carboxylates, hydrogen peroxide (640 µl of a 30 % solution, 6 mmole) and 700 mg sodium chlorite (80% grade, 7.5 mmole) were added (see Table 2). The pH was kept constant at pH 5 using 0.5 M NaOH
- 15 (pH stat.). After reaction, the aldehyde carboxy starch was purified by filtration and washing with water and the product was subsequently freeze-dried.

Table 2: Conversion of DAS to MACS

Sample	Added hydrogen peroxide solution (30%) (µl)	Added sodium chlorite (80%) (mg)	% aldehydes oxidised to carboxylates
Ac5	320	350	5
Ac10	640	700	10
Ac15	960	1050	15

b) Application as wet strength additive

- 20 Sheets were prepared as in example 8. The addition levels were 10 mg/g MACS and 10 mg/g PAE. The results are presented in Figure 3.

Example 4

- 25 Dialdehyde cellulose (oxidation degree 100%) was prepared by adding 6.6 g sodium periodate (31 mmole) to a slurry of 5.0 g (dry weight) cellulose (31 mmole) in 100 ml water which was brought to pH 5 with diluted acetic acid and cooled to 4°C. The mixture was stirred for 1 week at 4°C in the absence of light. The obtained product was isolated by filtration and washed with water until iodate could no longer be detected by reaction with
- 30 potassium iodide.

To obtain MACC, the dialdehyde cellulose was reslurried in 100 ml water and half of the aldehydes were further oxidised to carboxylates. To achieve this, sodium bromide (0.5 g) was added and then peracetic acid (0.6 M) was added portion-wise (52 ml of a 0.6 M solution). The pH was kept constant at pH 5 using 0.5 M NaOH (pH-stat.). After reaction, the aldehyde carboxy cellulose was purified by membrane filtration (molecular cut-off 5000 MW) and freeze-dried.

Sheets were prepared as in example 8. The results are presented in Figure 3.

Example 5

MACS with an oxidation degree of 10 % was prepared as described in example 1. This material was added to pulp (10 mg/g) together with cationic dialdehyde starch (10 mg/g). Sheets were prepared as in example 8. The results are presented in Figure 3.

Example 6

MACS with an oxidation degree of 10 % was prepared as described in example 1. 1 g of this material was suspended in water and Girard's reagent ($\text{NH}_2\text{NHCOCH}_2\text{N}^+(\text{CH}_3)_3$, betaine hydrazide, 100 mg for 10% cationisation) was added. The solution was stirred for 2 hours at 40°C and was subsequently freeze dried. A cationic MACS derivative was obtained. This sample was added to pulp (addition level 10 mg/g), and sheets were prepared as in example 8. The cationic MACS derivative adsorbs onto the fibres and gives wet strength. When added together with PAE (10 mg/g), the performance increased with lowering of the content of cationic groups (see Figure 4).

Example 7

6-Aldehyde starch was prepared by a TEMPO-mediated oxidation of starch. 5.0 g (dry weight) starch (31 mmol) was gelatinised in 250 ml water. TEMPO (65 mg) and horseradish peroxidase (100 mg) were added. The pH of the solution was adjusted to 5.0 using diluted acetic acid. Hydrogen peroxide (3.75 ml of a 30 % solution, 33 mmole) was diluted to a volume of 125 ml and was added gradually at a rate of 5 ml/hour. The reaction time was 25 hours at room temperature. Adjustment of the pH during reaction was not necessary. The product was purified by membrane filtration (molecular cut-off 5000 MW) and freeze-dried.

1 g of this material was redissolved in water and Girard's reagent (100 mg for 10% cationisation) was added. The solution was stirred for 2 hours at 40°C and was subsequently freeze dried again. A cationic 6-aldehyde starch was obtained. This sample

was added to pulp (addition level 10 mg/g) together with PAE (10 mg/g). Sheets were prepared as in example 8. The results are shown in Figure 5.

Example 8

5 *Sheet making with derivatives of the invention*

1. Refining

500-530 grams of Östrand TCF pulp is diluted to 12 litres and refined to 25 SR° by a Laboratory refiner R1L, Escher Wyss. The pulp, when refined, is about 40 g/L so it is diluted to the concentration of 3 g/L.

10 *2. Dynamic sheet former, Formette*

A wire of 0,4 m² is used and we want the Grammage to be 30 g/m².

The pulp is poured into the beater and the wet strength additive is added during stirring for 5 minutes. If PAE is added, it is added after five minutes and the pulp is stirred again for two minutes. Drum speed 1400 rotations/min, dewatering 30 sec.

15 *3. Press*

An absorbent paper is put over the sheet and the wire is taken off. Before pressing another absorbent paper is put over the sheet, so the sheet is between the two absorbent papers. The sheet is pressed at 0,5 bar once. To be able to compare sheets with each other, two sheets of the same composition are made but pressed at two different pressures, 0,5 bar and 5 bar. In
20 this way we can compare them at the same density 400 g/cm³.

4. Drying

The sheet is cut into four pieces and dried two and two with a fixed point for three minutes at a temperature of 140 °C.

5. Cutting

25 The sheet is cut into 15 mm strips for testing of dry and wet strength.

100*100mm is also cut out for measuring the thickness and Grammage.

6. Conditioning

The strips which wet strength is going to be tested are placed in a heating chamber, 105° C for 10 minutes. Then both the strips for wet and dry strength are placed in a climate room,
30 temperature 23°C, moisture 50% for four hours.

7. Grammage and thickness

100*100 mm pieces of the sheet is used for measuring the Grammage and thickness.

Grammage is measured on a regular balance on 4 layers to get an average.

Thickness is also measured on four layers and on five different spots to get a good average.

8. Tensile strength measurement

The strength both wet and dry is measured in an Instron SCAN-P58:86.

Five 15-mm strips are measured to get an average.

When measuring the wet strength the strip is soaked for 15 sec in tap water.

5

Example 9:

Large-scale preparation of MACS and application in a full scale tissue paper machine

The preparation of MACS with 15% of the aldehydes oxidised to carboxylic acids, as described in Example 1, was scaled up to 40 kg scale.

10 In the first step, 100% dialdehyde starch (DAS) was prepared. Sodium periodate (27 kg) was dissolved in 200 L water in a double-walled 300 L vessel equipped with a mechanical stirrer. The solution was cooled to 5°C. To this solution, potato starch (25 kg, 20.5 kg dry matter) was added portion-wise, keeping the temperature below 10°C. The slurry was stirred for 24 hours at 5°C. Then, the sodium iodate salts were removed by decantation after
15 settling of the DAS. The granules were washed with deionised water until no sodium iodate could be detected with potassium iodide and sulphuric acid. This procedure was repeated once and one more time using 21 kg sodium periodate and 20 kg starch. The overall yield of dialdehyde starch was 47 kg of DAS (82 % of theory, due to some losses during the washing procedure).

20 In the second oxidation step, MACS was prepared. DAS (11.75 kg) was slurried in about 150 L deionised water in a 300 L double-walled vessel. Sodium bromide (1.41 kg) was added and subsequently peracetic acid (7.07 kg, 39% activity) was added slowly using a pump running at 20 mL/min. The pH maintained between 4.7 and 5.3 by a pH controller adding 4 M NaOH. The temperature was kept between 15°C and 20°C. After all chemicals
25 were added, the solution was stirred overnight to ensure complete reaction. After reaction, the volume was reduced and part of the sodium acetate salts formed during reaction were removed using a membrane filtration unit (exclusion limit of 10000 D) to obtain a solution containing about 10 % MACS. This procedure was executed 4 times, and the products were mixed. The reaction yield of MACS in the second oxidation step was 42 kg (87 % of
30 theoretical).

A solution (490 kg) containing 8.6 % MACS was obtained. The polymer obtained in this way had similar characteristics regarding molecular weight and charge density as the material described in Example 1.

A tissue paper containing MACS was produced at a paper machine. See Example 10.

35

Example 10: Application in a full scale tissue paper machine

With the MACS thus prepared (see Example 9), tissue paper was made on an industrial scale (continuous process) and the properties of the tissue were compared to those obtained with conventional wet strength agents.

- 5 Three kinds of tissues were made using the following composition of pulp: 65% TCF pulp (total chlorine free pulp) and 33% HTCTM pulp (high temperature chemi-thermo-mechanical pulp).

The first run was the reference, in which only PAE (9 kg/ton pulp) was applied. The second run was prepared using PAE (9 kg/ton pulp) and CMC, Hercobond C129 with a degree of
10 substitution of 0.65-0.9, (1.7 kg/ton pulp). In the third run, PAE (9 kg/ton) and 1.7 kg MACS per ton were used. The results with regard to the dry strength, wet strength, and wet tensile index are summarised in Table 3.

15 *Table 3. Wet and dry strength properties of tissue paper with PAE, PAE/CMC and PAE/MACS, respectively.*

Run	Tissue samples	Dry strength (Nm/g)	Wet strength (Nm/g)	Tensile strength index (%)
1	PAE(ref.)	8.9	2.5	28.1
2	PAE/CMC	11.6	3.2	27.3
3	PAE/MACS	10.8	3.2	29.6

As can be seen from Table 3, both MACS and CMC improve the properties of the tissue with regard to wet and dry strength and CMC and MACS exhibit the same properties.


Claims

1. Use of a water-soluble or water-dispersible polymer having a molecular weight of at least 800, containing 0.25-2.25 aldehyde groups per recurring unit of the polymer and/or at least 5 aldehyde groups per molecule and containing at least 1 anionic group per molecule, the ratio of aldehyde groups to anionic groups being higher than 0.75:1, as a wet strength additive.
2. Use according to claim 1, in which the degree of substitution for aldehyde groups is 0.1-2.95 per recurring unit of the polymer, and the degree of substitution for anionic groups is 0.03-1.0 per recurring unit of the polymer.
3. Use according to claim 1, in which the degree of substitution for aldehyde groups is 0.25-2.25 per recurring unit of the polymer, and the degree of substitution for anionic groups is 0.05-0.4 per recurring unit of the polymer.
4. Use according to any one of claims 1-3, in which the anionic groups comprise carboxylic groups.
5. Use according to any one of claims 1-4, in which the polymer is a polysaccharide.
6. Use according to claim 5, in which the polymer is starch or cellulose or a starch- or cellulose-derived polymer.
7. Use according to claim 5 or 6, in which the aldehyde groups and the anionic groups are present as a result of oxidation of dihydroxyethylene moieties of recurring monosaccharide units.
8. Use according to claim 5 or 6, in which the aldehyde groups and the anionic groups are present as a result of oxidation of hydroxymethyl moieties of monosaccharide units.
9. Use according to any one of the preceding claims, in which anionic groups are present as a result of carboxymethylation.
10. Use according to any one of the preceding claims, in which the polymer further contains cationic groups with a degree of substitution of 0.01-0.50.

11. Carbohydrate derivative containing 0.10-2.95 aldehyde groups, and 0.03-1.0 anionic groups and 0.01-0.50 cationic groups per recurring unit.
12. A wet strength composition containing 10-90% of a carbohydrate derivative containing 0.10-2.95 aldehyde groups, and 0.03-1.0 anionic groups per recurring unit, and 90-10% of a cationic polymer, the percentages being based on the total of carbohydrate derivative and cationic polymer.
13. A cellulosic fibre treated with a polymer as defined in any one of claims 1-11, or with a mixture according to claim 12.


Fig 1

MACS with varying carboxylic acid content
(10kg/ton; in the presence of 10kg/ton PAE)



2/6

Fig 2
MACS together with cationic polymers



3/6

Fig 3

MACS, MACC
(10 kg/ton; in the presence of 10 kg/ton cationic polymer)





Fig 4


cationic MACS (A10 with varying cationic content)
(addition level: 10kg/ton)



5/6

Fig 5

cationic 6AS
(10 kg/t in the presence of 10 kg/t PAE)



6/6




Fig 6

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 01/00343

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21H21/20 C08B15/00 C08B31/00 //D21H17:25,D21H17:28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H C08B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 11046 A (HERCULES INC) 2 March 2000 (2000-03-02) claims 1,6,14,25,59; examples ---	1,4,10, 13
A	US 4 675 394 A (JOBE PATRICK G ET AL) 23 June 1987 (1987-06-23) the whole document ---	1,5,6, 11-13
A	EP 0 283 951 A (NAT STARCH CHEM CORP) 28 September 1988 (1988-09-28) page 4, line 47 -page 5, line 24; claims 1,2,5,15,16 ---	1,5,6, 11-13
A	EP 0 232 851 A (NAT STARCH CHEM CORP) 19 August 1987 (1987-08-19) page 4, line 5 -page 7, line 15; claims 1,2,5-8 ---	1,5,6, 11-13
-/-		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

6 September 2001

Date of mailing of the international search report

17/09/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Songy, 0

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 01/00343

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 958 187 A (MARINACK ROBERT J ET AL) 28 September 1999 (1999-09-28) column 5, line 32 -column 7, line 50 -----	11-13

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT
information on patent family members

International Application No
PCT/NL 01/00343

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
WO 0011046	A	02-03-2000	AU	5489999 A	14-03-2000
US 4675394	A	23-06-1987	AT	37884 T	15-10-1988
			AU	558885 B	12-02-1987
			AU	4615585 A	20-02-1986
			BR	8503957 A	03-06-1986
			DE	3565543 D	17-11-1988
			EP	0175113 A	26-03-1986
			ES	546195 D	16-01-1986
			ES	8604267 A	01-06-1986
			FI	853152 A,B,	18-02-1986
			JP	1920543 C	07-04-1995
			JP	6049722 B	29-06-1994
			JP	61112091 A	30-05-1986
			US	4983748 A	08-01-1991
			US	4703116 A	27-10-1987
			CA	1237124 A	24-05-1988
			US	4731162 A	15-03-1988
			US	4741804 A	03-05-1988
			ZA	8506141 A	28-05-1986
EP 0283951	A	28-09-1988	US	4788280 A	29-11-1988
			CA	1305961 A	04-08-1992
			DE	3883818 D	14-10-1993
			DE	3883818 T	10-03-1994
			JP	1242601 A	27-09-1989
			JP	1902670 C	08-02-1995
			JP	6025201 B	06-04-1994
EP 0232851	A	19-08-1987	US	4703116 A	27-10-1987
			AT	65783 T	15-08-1991
			AU	594744 B	15-03-1990
			AU	6882687 A	20-08-1987
			DE	3771739 A	05-09-1991
			FI	870631 A,B,	15-08-1987
			JP	1628834 C	20-12-1991
			JP	2055441 B	27-11-1990
			JP	62246902 A	28-10-1987
			US	4741804 A	03-05-1988
			US	4804769 A	14-02-1989
US 5958187	A	28-09-1999	EP	0672787 A	20-09-1995
			FI	951275 A	19-09-1995
			CA	2144838 A	19-09-1995